SHERWIN-WILLIAMS.

Technical Data Sheet

Issue Date: June 16

FF810

Acid Catalysing Clear Sanding Sealer

DESCRIPTION & USES

Two-component acid catalysed (amino-alkyd and cellulose) sanding sealer for furniture and fittings. FF810 is formulated with low formaldehyde binders and low toxicity solvents to reduce risks with usage (contains NO aromatic hydrocarbons or Butanol). This high build sealer provides a sound base for top-coating and allows easy sanding

for demanding production schedules.

Recommended

Application: For use as a sealer under DM307 and DC810. Furniture, joinery, shop-fitting, wardrobe

& kitchen doors, commercial interiors.

N.B Not recommended for use in wet areas (i.e kitchen benchtops, vanity tops etc)

DRY FILM PROPERTIES

Colour: Clear

N/A Gloss:

WET PROPERTIES

Solid content: 44% (approx)

Viscosity in drum: 75 seconds Ford Cup 4 @ 20°C

12 months in sealed containers Shelf life:

APPLICATION

Method: Spraying conventional, curtain coating, roller coating

Mixing Ratio: 10 parts FF810 to 1 part DV311 hardener

Thinning: DT8900 or BECKER22 at 10-30%

(Depending on type equipment used)

Pot Life: 2-3 days (approx), may be extended if kept in a cool area

4-6 hours at 20°C or 25-30 minutes at 70°C Drying:

NOTES

Not recommend for use when sealing Beech and Tasmanian Blackwood

Do not use under DC1516 or DM1516

Contact us for further information

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L Tel (08) 9206 0220 Fax (08) 9206 0974 **NSW:** CROMA COATINGS Tel (02) 9533 9122 Fax (02) 9533 9299 VIC: CROMA COATINGS VICTORIA Tel (03) 9768 2312 Fax (03) 9768 2389 QLD: CROMA COATINGS QUEENSLAND Tel (07) 3386 1000 Fax (07) 3386 1003

Email info@22croma.com.au Web www.22croma.com.au